


**Description :**

Transparent, slip modified BOPP film for printing and lamination

**Features and applications :**

- \* Both sides corona treated
- \* Good machinability
- \* Excellent adhesion to water based inks and UV lamination adhesives
- \* Excellent gloss and clarity
- \* Excellent performance in film-to-film, film-to-paper and cardboard laminations

**Available gauge(s) (µm) :** 12,19



Properties	Unit		Technical Values	Test Method
<b>Thickness</b>	µm		12	ASTM D 2673
<b>Yield</b>	m2/kg		91,6	ASTM D 2673
<b>Haze</b>	%		=< 2,5	ASTM D 1003
<b>Gloss</b>	%	F	90	ASTM D 2457
<b>Dimensional stability</b>	%	MD	-3	ASTM D 1204
	%	TD	-1	
<b>Tensile strength at break</b>	kg/mm <sup>2</sup>	MD	14	ASTM D 1003
	kg/mm <sup>2</sup>	TD	30	
<b>Elongation</b>	%	MD	135	ASTM D 882
	%	TD	50	
<b>C.O.F</b>		BB	=< 0,5	ASTM D 1894
<b>Surface tension</b>	dyne/cm	F	38	ASTM D 2578
	dyne/cm	B	38	

F: Front - B: Back

This film complies with the EC and FDA food contact regulations. Detailed documentation is available on your request.

All the information contained in this datasheet is supplied at the best of our knowledge and must not be construed as a guarantee. Since the circumstances and processes used in the application of our product are beyond our control, our guarantee remains within the limits of the generic conditions of supply of the product itself. Business Development and Customer Solutions Department is available to supply upon request all the updated recommendations relevant to the best converting and processing techniques for the product. Also, different film thicknesses and properties are available upon request.



**Date** : 27.02.2024

Main Plant : Organize Sanayi Bölgesi, Manisa 45030 - Tel : +90 236 226 22 00 (pbx) Fax : +90 236 233 25 25 e-mail : info@polinas.com.tr

Istanbul Office : Kısıklı Mah., Alemda Cad. No:60 Masaldan Merkezi, F Blok Kat:1, 34692 Üsküdar / İstanbul 34692 - Tel: +90 850 209 19 00 Fax: +90 236 233 25 25