


**Description :**

Solid white, non-heat sealable BOPP film for adhesive tapes

**Features and applications :**

- \* One side corona treated
- \* Low elongation in machine direction property
- \* Cost-saving converting process due to its natural solid white color
- \* Ideal whiteness and gloss
- \* Treated side is good for water based acrylic adhesive coating and hot-melt applications

**Available gauge(s) (µm) :** 20,28



Properties	Unit	Technical Values		Test Method
<b>Thickness</b>	µm	20	28	ASTM D 2673
<b>Yield</b>	m2/kg	51	36,4	ASTM D 2673
<b>TT</b>	%	40	40	ASTM D 1003
<b>Gloss</b>	%	F	60	ASTM D 2457
<b>Dimensional stability</b>	%	MD	-3	ASTM D 1204
	%	TD	-1	
<b>Tensile strength at break</b>	kg/mm <sup>2</sup>	MD	14	ASTM D 882
	kg/mm <sup>2</sup>	TD	30	
<b>Elongation</b>	%	MD	135	ASTM D 882
	%	TD	50	
<b>C.O.F</b>		BB	=< 0,5	ASTM D 1894
<b>Surface tension</b>	dyne/cm	F	>= 36	ASTM D 2578

TT: Total Light Transmission - F: Front - B: Back

This film complies with the EC and FDA food contact regulations. Detailed documentation is available on your request.

All the information contained in this datasheet is supplied at the best of our knowledge and must not be construed as a guarantee. Since the circumstances and processes used in the application of our product are beyond our control, our guarantee remains within the limits of the generic conditions of supply of the product itself. Business Development and Customer Solutions Department is available to supply upon request all the updated recommendations relevant to the best converting and processing techniques for the product. Also, different film thicknesses and properties are available upon request.



**Date** : 15.03.2026

Main Plant : Organize Sanayi Bölgesi, Manisa 45030 - Tel : +90 236 226 22 00 (pbx) Fax : +90 236 233 25 25 e-mail : info@polinas.com.tr

Istanbul Office : Kısıklı Mah., Alemda Cad. No:60 Masaldan Merkezi, F Blok Kat:1, 34692 Üsküdar / İstanbul 34692 - Tel: +90 850 209 19 00 Fax: +90 236 233 25 25