

**Description :**


PKRD is one side matte, other side is chemically treated BOPET film.

Features and applications :

- * One side is chemically treated
- * Excellent machineability
- * Good dimensional stability
- * Superior ink adhesion with different inks and coating materials
- * One side is matte
- * Excellent matte finish surface
- * Excellent stiffness
- * PKRD is a retortable film (lab test 120°C, 30 min)

Available Gauge (s) (µm) : 12

PKRD needs to be stocked in a close warehouse and preserved from the light. Polinas will not accept any responsibility for material older than 1 year from the delivery



| Properties | Unit | Technical Values | Test Method |
|---------------------------|------------|------------------|-------------|
| Thickness | µm | 12 | ASTM D 2673 |
| Yield | m2/kg | 59,9 | ASTM D 2673 |
| Haze | % | 45 | ASTM D 1003 |
| Dimensional Stability | % MD | 1,5 | ASTM D 1204 |
| | % TD | 1 | |
| Tensile Strength at Break | kg/mm2 MD | 22 | ASTM D 882 |
| | kg/mm2 TD | 25 | |
| Elongation | % MD | 130 | ASTM D 882 |
| | % TD | 110 | |
| COF | BB | =< 0,5 | ASTM D 1894 |
| OTR (23C, 0%RH) | cm3/m2/24h | 110 | ASTM D 3985 |
| WVTR (38C, 90%RH) | gr/m2/24h | 50 | ASTM F 1249 |

F: Front - B: Back

This film complies with the EC and FDA food contact regulations. Detailed documentation is available on your request.

All the information contained in this datasheet is supplied at the best of our knowledge and must not be construed as a guarantee. Since the circumstances and processes used in the application of our product are beyond our control, our guarantee remains within the limits of the generic conditions of supply of the product itself. Business Development and Customer Solutions Department is available to supply upon request all the updated recommendations relevant to the best converting and processing techniques for the product. Also, different film thicknesses and properties are available upon request.



Date : 28.02.2025

Main Plant : Organize Sanayi Bölgesi, Manisa 45030 - Tel : +90 236 226 22 00 (pbx) Fax : +90 236 233 25 25 e-mail : info@polinas.com.tr
Istanbul Office : Kısıklı Mah., Alemdag Cad. No:60 Masaldan s Merkezi, F Blok Kat:1, 34692 Üsküdar / İstanbul 34692 - Tel: +90 850 209 19 00 Fax: +90 236 233 25 25

<http://www.polinass.com>